

Concrete Surface Retarder

ETCHING FLUID

TECHNICAL DATA

1.0 DESCRIPTION

ETCHING FLUID is a water based concrete surface retarder which when applied to formwork, prevents concrete poured against it from setting to a depth of 5-10mm, for up to 48 hours. This allows the retarded concrete to be removed by hose after the forms have been stripped, resulting in an exposed aggregate finish.

2.0 PHYSICAL PROPERTIES

2.1. Colour	Transparent Blue
2.2. Specific Gravity	1.1
2.3. Flash Point	>100°C
2.4. Viscosity	Low to medium
2.5. Toxicity	Harmful substance. Contains Methylated Sprits.
2.6. D.G. Classification	Not classified.
2.7. Shelf Life	Unlimited in sealed drums as supplied
2.8. Coverage	5 - 6 m ² / litre

3.0 USES

- ETCHING FLUID is used to create a mechanical key on a concrete surface which is to have more concrete poured against it. An example of this is where ETCHING FLUID is painted on stop ends which confine individual pours of a floor slab. When the stop ends are removed and the retarded concrete is washed off, the resultant exposed aggregate finish makes an excellent key for the next pour.
- ETCHING FLUID can also be used to create an architectural exposed aggregate finish on columns, beam panels, pavers and any other formed concrete surface.

4.0 APPLICATION

- ETCHING FLUID is applied by brush, roller or spray and preferably allowed to dry for about 1 hour before pouring concrete.
- ETCHING FLUID has no release value so that forms should get normal treatment with Discrete before application. This will prevent any build up on the stripped forms sticking after the retarded concrete has eventually set.
- Normal concrete placed at normal temperatures should be removed within 48 hours. High strength concrete or concrete placed at high temperature will not be retarded for as long and consequently should have forms stripped and retarded concrete removed within 24 hours or sooner.
- Treated formwork will withstand a shower, but not heavy rain, as the ETCHING FLUID is soluble in water.

5.0 PACKAGING

20 litre pails, 210 litre drums.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



FBS0702